SABIC Innovative Plastics™

Lexan* Exell D FR Sheet



Description

Lexan* Exell*D FR sheet is a transparent polycarbonate sheet with proprietary UV protection on both sides offering excellent weathering properties. With its excellent impact resistance it is an excellent candidate for a wide variety of building and construction applications. Lexan ExelID FR sheet can be easily cold formed into gentle curves which makes it a good material choice for skylights, covered walkways, barrel vaults etc. Lexan ExelI DFR sheet is thermoformable and can be thermoformed into the desired geometry whilst retaining the UV resistant coating specially developed for weather resistant applications.

Typical Property Values

Property	Test Method	Unit	Value	
Physical				
Density	ISO 1183	g/cm³	1.23	
Water absorption, 23 °C / saturation	ISO 62	mg	10	
Mechanical				
Tensile stress at yield 50 mm/min	ISO 527	MPa	60	
Tensile modulus 1 mm/min	ISO 527	MPa	2300	
Tensile elongation, yield		%	6	
break		%	80	
Flexural strength. yield 2 mm/min	ISO 178	MPa	90	
Flexural modulus 2 mm/min	ISO 178	MPa	2300	
Impact				
Izod impact, unnotched 23°C	ISO 180/4U	kJ/m²	NB	
Izod impact, unnotched -30°C	ISO 180/4U	kJ/m²	NB	
Izod impact, notched 23°C	ISO 180/4A	kJ/m²	10	
Izod impact, notched -30°C	ISO 180/4A	kJ/m²	10	
Gardner impact, 20 °C	SABIC-Method	J	>40	
-40°C		J	>40	
Thermal				
Vicat Softening Temperature, rate B/120	ISO 306	°C	145	
HDT/Ae, 1.8 MPa edgew. 120*1*04/sp=100	ISO 75/Be	°C	127	
Thermal conductivity	ISO 8302	W/m°C	0.2	
Ball pressure test, 125 ± 2 °C	IEC 335-1		Pass	
Mold shrinkage	SABIC-Method	%	0.5-0.7	
Coeff. of Thermal Expansion	ASTM D696	1/ °C	7.10 ⁻⁵	
Optical				
Light transmission, 3 mm	ASTM-D1003	%	89	

These property values have been derived from Lexan* resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC- Innovative Plastics representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

* Trademarks of SABIC Innovative Plastics IP BV



Lexan* Exell D FR Sheet



Light Transmission Transparent Lexan Exell D FR sheet have excellent light transmission, between 84 and 87%. However for buildings in hot climates or with south facing aspects, Lexan Exell D FR is available in translucent bronze, grey and opal white. Lexan Exell D FR is essential opaque to all wave lengths below 385 nanometers. This useful shielding property can help prevent discoloration of sensitive materials placed under or behind Lexan Exell D FR sheet.

UV Protection

Lexan Exell D FR sheet has proprietary UV protected surfaces, giving excellent durability to outdoor weathering. This superior UV resistance and toughness of Lexan Exell D FR sheet is backed by a 10 years limited written warranty against yellowing, loss of light transmission and breakage.

Fire Performance

French Norm NF P92-505 M2 Classification are available for ExelID FR sheet transparent grades with thickness 2, 3, 4, 5, 8mm.

Product Availability

Lexan Exell D FR sheet is normally manufactured in the standard sizes listed below. Deliveries from stock or cut to size can be ordered via

our customer service organisation. Standard gauge in mm: Standard sizes: Masking: Standard color:

2 - 3 - 4 - 5 - 8 1250 x 2050 mm, 2050 x 3050 mm, 2050 x 6050 mm Top side: Coex. opal white PE/purple print, Bottom side: Coex. transparent foil clear code 112



Americas: SABIC Innovative Plastics Specialty Film & Sheet One Plastics Avenue Pittsfield, MA 01201 USA Tel. (1) (413) 448 5400 Fax. (1) (413) 448 7506 Toll free: 1-800 451 3147 Europe: SABIC Innovative Plastics Specialty Film & Sheet Plasticslaan 1 NL - 4612 PX Bergen op Zoom The Netherlands Tel. (31) (164) 292911 Fax. (31) (164) 293272

Pacific: SABIC Innovative Plastics Specialty Film & Sheet 1468 Nanjin Road (W) 26th Floor, United Plaza 200040 Shanghai, China Tel. (86) 21 3222 4500 Fax. (86) 21 6289 8998

THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT http://www.sabic-ip.com AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC Innovative Plastics is a trademark of Sabic Holding Europe BV

* Trademark of SABIC Innovative Plastics IP BV

www.sabic-ip.com

Latest update (11/07)