

Lexan* Margard* MRX Sheet

Product Datasheet

Description

High abrasion resistant - weatherable, Lexan* Margard* MRX sheet is a both-side hard coated polycarbonate sheet offering excellent abrasion resistance, excellent dimensional stability, impact resistance, optical clarity . Typical applications can be sound-barriers, separations screens and flat glazing systems needing impact resistance combined with chemical and abrasion resistance .

Typical Property Values ♦

Property	Test Method	Unit	Value
Physical			
Density ³⁾	ISO 1183	g/cm ³	1.20
Water Absorption 23°C/Sat	ISO 62	%	0.35
Optical			
Light transmission (<3mm)	ASTM D1003	%	89.5
Light transmission (3-6mm)	ASTM D1003	%	89.5-86
Taber abrasion ¹⁾			
CS10F, 500g, 500 cycles (ASTMD1044)	ASTM D1003	%haze	≤12
Mechanical			
Tensile stress, yield ²⁾	ISO 527	MPa	60
Tensile modulus ²⁾	ISO 527	MPa	2350
Elongation, yield ²⁾	ISO 527	%	6
Elongation, break ²⁾	ISO 527	%	100
Flexural strength, yield ³⁾	ISO 178	Mpa	90
Flexural modulus ³⁾	ISO 178	MPa	2300
Thermal			
Vicat Softening Temp, Rate B /120 ³⁾	ISO 306	°C	145
HDT/Be, 0.45 MPa ³⁾	ISO 75/Be	°C	138
Thermal Expansion ³⁾	ISO 11359-2	1 / °C	7x10 ⁻⁵

1) The target value for this property is 10% however, the reproducibility of the test method between laboratories is variable in that single, individual measurements can be as high as 12%.

2) Coating will crack before specified value.

3) Property of the base sheet and/or uncoated side.

♦ These property values have been derived from Lexan* resin data for the material used to produce this sheet product.



GE Advanced Materials Specialty Film & Sheet

Lexan* Margard* MRX Sheet Product Datasheet

Chemical resistance

Lexan* Margard* MRX sheet has high resistance at the coated side to many chemicals. In applications where it will come into contact with aggressive chemicals, specific (application related) testing of the material is strongly recommended.

Assembling

Parts made from Lexan Margard MRX sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these techniques can cause environmental stress cracking, please ensure that you have carried out tests regarding its suitability for your applications or end use.

Product Availability **)

gauge (mm)	width (mm)	length (mm)	color
3.00	2000	3000	112
4.00	2000	3000	112
6.00	2000	3000	112
8.00	2000	3000	112
9.50	2000	3000	112
12.0	2000	3000	112

***) From 3.00mm up to and including 12.00mm , other dimensions upon request and are subject to minimum order quantities.

Installation

For some applications the ripple orientation may play an important role while installing the Lexan Margard MRX sheet. The ripple orientation is indicated for this purpose on the protective masking.

Cleaning

- Never scrape the sheet with squeegees, razorblades or other sharp instruments.
- Do not clean Lexan Margard MRX sheet products under sunny and/or hot environments.
- For removal of paints, marker pen inks, lipstick, and graffiti etc., we recommend to use Butyl Cellusolve and products mentioned in the Lexan solid sheet processing manual. Do not use abrasive or alkaline cleaners.
- To remove labels, stickers etc. the use of kerosene, naphta or white spirit is generally effective.
- After having cleaned the Lexan Margard MRX sheet a final wash should be made, using a mild soap solution and finishing with a thorough rinsing with cold water.

Americas:

GE Advanced Materials
Specialty Sheet & Film
One Plastics Avenue
Pittsfield, MA 01201
USA
Tel. (1) (413) 448 7110
Fax. (1) (413) 448 7506

Europe:

GE Advanced Materials
Specialty Sheet & Film
Plasticslaan 1
PO Box 112
NL - 4600 AC Bergen op Zoom
The Netherlands
Tel. (31) (164) 292742
Fax. (31) (164) 291986

Pacific:

GE Advanced Materials
Specialty Sheet & Film
1266 Nanjin Road (W)
16th Floor, Plaza 66
200040 Shanghai
China
Tel. (86) 21 6288 1088
Fax. (86) 21 6288 0818

For more information call:

(800) 451-3147

Visit us online at:
www.geadvancedmaterials.com

©2005 General Electric Company
All Rights Reserved

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF THE BUSINESSES MAKING UP THE GE ADVANCED MATERIALS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ARE SOLD SUBJECT TO GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GE ADVANCED MATERIALS MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING GE ADVANCED MATERIALS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GE ADVANCED MATERIALS' STANDARD CONDITIONS OF SALE, GE ADVANCED MATERIALS AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of GE Advanced Materials' products, materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating GE Advanced Materials' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GE Advanced Materials' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GE Advanced Materials. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* Trademark of General Electric Company

